

# Gold Rush

## Handling Instructions

### The Ultimate Premium Lightweight Polyester Glazing Putty

#### DIRECTIONS FOR USE

**Mixing:** Using a clean tool, transfer the desired amount of putty to a clean non-absorbent surface. Knead the “hardener” and add in proportion to the amount supplied. Using a separate clean tool, mix the filler and hardener together until a uniform color mix results. When mixing, use a circular rubbing motion to avoid air entrapment. Do not whip or stir air into mixture.

**Application:** In cold temperatures or high humidity, warm the area to be repaired- to eliminate all traces of microscopic moisture. Then, with firm pressure, apply an initial thin layer of putty. Reapply the putty to a desired thickness and contour. Restroke the area slowly for maximum smoothness. On larger areas, drill small holes to “anchor” the putty. Force the putty through these holes on the initial application. Do not return any mixed filler to the putty can.

**Finishing:** The gel time is 4-7 minutes depending on the room temperature. In another 5 minutes initial “high spot” filling can be started followed by feather edge filling with positive adhesive. Sand to prepare for priming and finishing coats.

**Note:** DO NOT wipe over cured putty with solvent or thinner before priming.

**Caution: HARMFUL IF INGESTED.** If ingested, do not induce vomiting. Consult a physician. **VAPOR HARMFUL.** Avoid prolonged breathing of vapor; if headache or nausea occur, remove to fresh air. **SKIN AND EYE IRRITANT.** Avoid prolonged or repeated contact with skin. In case of contact, flush skin and eyes with plenty of water. **COMBUSTABLE.** Keep away from heat, sparks, and open flame. Keep lip closed while not in use. **KEEP OUT OF REACH OF CHILDREN.** Store in cool dry place.