

## Z-Glaze Polyester Glazing Putty Handling Instructions

Stain Free•Tack-Free•Exceptionally Smooth  
Easy Spreading•Easy Sanding

### Directions for Use

Area must be sanded and void of dirt, wax, grease, oil or rust. Surface must be completely dry and moisture free before application. For best results use at temperatures above 68°F. Place required amount of “Z-Glaze” on a clean surface (non fibrous). For every 4 ozs of “Z-Glaze” add approximately 2.25 grams or approximately one quarter of a teaspoon of Blue Cream Hardener. Mix thoroughly and apply to desired area. Never return mixed material to can. Do not apply over fresh application of acrylic, lacquer primer surfacer or top-coats.

Approximate setting time is 4-5 minutes. Spread a thin layer not to exceed 1/8 of an inch to the mixed material over the surface. Apply additional layers to the surface building slightly to allow for sanding. Sandable in 15-20 minutes with 120-180 grit paper to start. Finish sanding with 220-400 grit prior to priming or sealing. Refer to paint manufacturer’s instructions for top coat application.

#### For Professional Use Only

**Caution: Flammable Liquid and Vapor. Vapor Harmful**

**Keep away from heat or open flames. Use only with adequate ventilation. Avoid prolonged exposure to vapors. HARMFUL IS SWALLOWED. Do not take internally. If swallowed, do not induce vomiting; call a physician. Keep away from heat, sparks, open flame and clothing. Avoid contact with eyes. In case of contact, flush with running water for at least 15 minutes. Store in a cool, dark place with lid on.**

**KEEP OUT OF REACH OF CHILDREN.**